

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions,  
and listings, of claims in the application:

LISTING OF CLAIMS:

1. (currently amended) A paper feed roller comprising:

a rotary shaft, and

a cylindrical roller ~~that comprises a mixture of~~  
~~hydraulic composition comprising a hydraulic powder and a non-~~  
~~hydraulic powder and a workability improver, said cylindrical~~  
~~roller portion being integrated with an outer periphery of the~~  
rotary shaft;

wherein the ~~workability improver is a material that has~~  
~~a property of improving moldability, mold-releasability,~~  
~~cutting/grinding workability, and grinding accuracy of a molded~~  
~~body obtained from the hydraulic composition~~ cylindrical roller  
comprises a mixture of:

a hydraulic composition comprising a hydraulic powder;

a non-hydraulic powder; and

one of a powder and an emulsion of at least one resin  
selected from the group consisting of: vinyl acetate resin, a  
copolymer resin with vinyl acetate, acrylic resin, a copolymer  
resin with acryl, styrene resin, a copolymer resin with styrene,  
and an epoxy resin.

2. (original) The paper feed roller set forth in claim 1, wherein the rotary shaft is constituted by two rotary shaft portions, said two rotary shaft portions are aligned with each other and axially inwardly inserted integrally into central portions of respective opposite end faces of the cylindrical roller portion from opposite sides such that the rotary shaft portions are concentric with an outer peripheral face of the cylindrical roller portion.

3. (previously presented) The paper feed roller set forth in claim 1, wherein the cylindrical roller portion is formed by connecting a plurality of cylindrical molded bodies in a direction of the rotary shaft.

4. (original) The paper feed roller set forth in claim 3, wherein at least one set of two adjacent cylindrical molded bodies connected is connection-reinforced with a connecting core rod extending over the two cylindrical molded bodies.

5. (previously presented) The paper feed roller set forth in claim 3, wherein connecting end portions of the cylindrical molded bodies to be connected to each other have interengaging shapes, and said cylindrical molded bodies are connected by engagement at said end portions.

6. (previously presented) The paper feed roller set forth in claim 1, wherein the hydraulic composition comprises 100 parts by weight of a mixed powder and 2 to 18 parts by weight of a workability improver, said mixed powder comprising 50 to 90 wt% of a hydraulic powder, and 10 to 50 wt% of a non-hydraulic powder having the average particle diameter smaller than that of the hydraulic powder by an order of one digit or more.

7. (cancelled)

8. (previously presented) A method for producing a paper feed roller, comprising the steps of:

forming a plurality of cylindrical molded bodies by press molding a mixture of a hydraulic composition comprising a hydraulic powder and a non-hydraulic powder and a workability improver, each of the cylindrical molded bodies having a hole at a central portion through molding the hydraulic composition,

releasing, curing and hardening the molded bodies,

inserting a rotary shaft through the holes of the plurality of cylindrical molded bodies, and

connecting adjacent said cylindrical molded bodies, and thereby integrally forming a cylindrical roller portion around an outer peripheral surface of the rotary shaft;

wherein the workability improver is a material that has a property of improving moldability, mold-releasability,

cutting/grinding workability, and grinding accuracy of the molded bodies.

9. (original) The paper feed roller-producing method set forth in claim 8, wherein connecting end portions of the cylindrical molded bodies to be connected to each other are molded to have interengaging shapes, and said cylindrical molded bodies are connected by engagement at said end portions.

10. (previously presented) A method for producing a paper feed roller, comprising the steps of:

forming a plurality of cylindrical green press molded bodies each having a hole at a central portion by press molding a mixture of a hydraulic composition comprising a hydraulic powder and a non-hydraulic powder and a workability improver,

releasing the green press molded bodies,

inserting a rotary shaft through the holes of the plurality of the cylindrical green press molded bodies,

connecting adjacent said cylindrical green press molded bodies, and

forming a cylindrical shaped body through curing and hardening the connected cylindrical green press molded bodies, so as to integrally form a cylindrical roller portion around an outer peripheral surface of the rotary shaft;

wherein the workability improver is a material that has a property of improving moldability, mold-releasability,

cutting/grinding workability, and grinding accuracy of the green molded bodies.

11. (original) The paper feed roller-producing method set forth in claim 10, wherein connecting end portions of the cylindrical molded bodies to be connected to each other are molded to have interengaging shapes, and said cylindrical molded bodies are connected by engagement at said end portions.

12. (previously presented) A method for producing a paper feed roller, comprising the steps of:

forming a cylindrical roller portion from a cylindrical press molded body shaped through press molding a mixture of a hydraulic composition comprising a hydraulic powder and a non-hydraulic powder and a workability improver,

releasing, curing and hardening the press molded body, arranging two rotary shaft portions to be concentric with an outer peripheral surface of the cylindrical roller portion, and

attaching the two rotary shaft portions to opposite end portions of the cylindrical roller portion, the two rotary shaft portions being aligned with each other, so as to form a rotary shaft by the two rotary shaft portions;

wherein the workability improver is a material that has a property of improving moldability, mold-releasability,

cutting/grinding workability, and grinding accuracy of the press molded body.

13. (previously presented) The paper feed roller-producing method set forth in claim 12, wherein the cylindrical molded body is formed such that holes are provided at center portions of opposite end portions of the cylindrical roller portion to make the holes concentric with the outer peripheral surface of the cylindrical roller portion, the two rotary shaft portions being inserted and integrally fixed into the holes, respectively, such that the rotary shaft portions are aligned with each other, and thereby the rotary shaft is constituted by the two rotary shaft portions.

14. (previously presented) The paper feed roller-producing method set forth in claim 12, wherein a screw portion is provided at one end portion of the rotary shaft portion, and the rotary shaft portion is attached to the end portion of the cylindrical roller portion by screwing the screw portion of the rotary shaft portion thereinto.

15. (previously presented) The paper feed roller-producing method set forth in claim 12, wherein a plurality of cylindrical press molded bodies are formed by molding the hydraulic composition, and releasing, curing and hardening the press molded body, and the cylindrical roller portion is formed by connecting the cylindrical press molded bodies together.

16. (original) The paper feed roller-producing method set forth in claim 15, wherein at least one set of adjacent cylindrical molded bodies are connected by a connecting core rod.

17. (previously presented) The paper feed roller-producing method set forth in claim 15, wherein connecting end portions of the cylindrical molded bodies to be connected to each other are molded to have interengaging shapes, and said cylindrical molded bodies are connected by engagement at said end portions.

18. (previously presented) A method for producing a paper feed roller, comprising the steps of:

press molding a mixture of a hydraulic composition comprising a hydraulic powder and a non-hydraulic powder and a workability improver to produce cylindrical green press molded bodies,

releasing the cylindrical green press molded bodies,  
forming a cylindrical roller portion from the cylindrical green press molded bodies,

arranging two rotary shaft portions to be concentric with an outer peripheral surface of the cylindrical roller portion, and

attaching the two rotary shaft portions to opposite end portions of the cylindrical roller portion, the two rotary shaft

portions being aligned with each other, so as to form a rotary shaft by the two rotary shaft portions, and

curing and hardening the roller portion while arranged on the rotary shaft;

wherein the workability improver is a material that has a property of improving moldability, mold-releasability, cutting/grinding workability, and grinding accuracy of the green press molded bodies.

19. (previously presented) The paper feed roller-producing method set forth in claim 18, wherein the cylindrical green molded bodies are formed such that holes are provided at center portions of opposite end portions of the cylindrical roller portion to make the holes concentric with the outer peripheral surface of the cylindrical roller portion, the two rotary shaft portions being inserted and integrally fixed into the holes, respectively, such that the rotary shaft portions are aligned with each other, and thereby the rotary shaft is constituted by the two rotary shaft portions.

20. (previously presented) The paper feed roller-producing method set forth in claim 18, wherein a screw portion is provided at one end portion of the rotary shaft portion, and the rotary shaft portion is attached to the end portion of the cylindrical roller portion by screwing the screw portion of the rotary shaft portion thereinto.



21. (previously presented) The paper feed roller-producing method set forth in claim 18, wherein a plurality of cylindrical press molded bodies are formed by molding the hydraulic composition and releasing the press molded bodies, connecting the cylindrical press molded bodies together, and the connected press molded bodies are cured and hardened, and the cylindrical roller portion is thereby formed.

22. (previously presented) The paper feed roller-producing method set forth in claim 19, wherein at least one set of adjacent said cylindrical green press molded bodies are connected by a connecting core rod.

23. (previously presented) The paper feed roller-producing method set forth in claim 21, wherein connecting end portions of the cylindrical molded bodies to be connected to each other are molded to have interengaging shapes, and said cylindrical molded bodies are connected by engagement at said end portions.

24. (new) The paper feed roller of claim 1, wherein the resin is vinyl acetate resin.

25. (new) The paper feed roller of claim 1, wherein the resin is a copolymer resin with vinyl acetate.

26. (new) The paper feed roller of claim 1, wherein the resin is acrylic resin.

27. (new) The paper feed roller of claim 1, wherein the resin is a copolymer resin with acryl.

28. (new) The paper feed roller of claim 1, wherein the resin is styrene resin.

29. (new) The paper feed roller of claim 1, wherein the resin is a copolymer resin with styrene.

30. (new) The paper feed roller of claim 1, wherein the resin is an epoxy resin.

---